

PAT-NO: JP411302119A  
DOCUMENT-IDENTIFIER: JP 11302119 A /  
TITLE: PRODUCTION OF ANTIMICROBIAL SILVER COLLOID  
PUBN-DATE: November 2, 1999

INVENTOR-INFORMATION:

NAME	COUNTRY
HIGOBASHI, HIROYOSHI	N/A
OKADA, HIROMICHI	N/A
HIRAI, HIDEFUMI	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
DAISO CO LTD	N/A

APPL-NO: JP10115148

APPL-DATE: April 24, 1998

INT-CL (IPC): A01N059/16, A01N025/04 , A01N025/12 , A01N025/22

ABSTRACT:

PROBLEM TO BE SOLVED: To disperse fine silver particles having an average particle diameter within a prescribed range and produce a colorless and transparent antimicrobial silver colloid useful for a coating material, a molding material, a catalyst, etc., by mixing the silver fine particles having a prescribed particle diameter with a resin and a peroxide in a dispersing medium such as water.

SOLUTION: This antimicrobial silver colloid is obtained by mixing silver fine particles having 8-200 nm particle diameter with a resin such as a methacrylic resin and a peroxide such as methyl ethyl ketone peroxide in a

dispersing medium such as water or a nonaqueous solution. The particle diameter of the dispersed silver fine particles in the colloid is 0.5-5 nm. The concentration of the silver fine particles contained in the colloid is preferably 10 ppm to 1 wt.%.

COPYRIGHT: (C)1999,JPO

DERWENT-ACC-NO: 2000-100667

DERWENT-WEEK: 200017

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Manufacture of anti-microbial silver colloid  
for coating material, moulding material and catalyst -  
involves mixing silver microparticles of specific mean  
particle diameter, resin and peroxide in aqueous or non-  
aqueous dispersion medium

PRIORITY-DATA: 1998JP-0115148 (April 24, 1998)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE
PAGES MAIN-IPC		
JP 11302119 A	November 2, 1999	N/A
005 A01N 059/16		

INT-CL (IPC): A01N025/04, A01N025/12 , A01N025/22 , A01N059/16

ABSTRACTED-PUB-NO: JP 11302119A

BASIC-ABSTRACT:

NOVELTY - Silver microparticles having a mean particle diameter of 8-200 nm, resin and peroxide are mixed in a dispersion medium of water or non-aqueous solution. The obtained silver colloid contains distributed silver microparticles having mean particle diameter of 0.5-5 nm.

USE - For coating material, molding material and catalyst and also used in internal equipment of infirmary and foodstuff factory.

ADVANTAGE - The obtained colloid is colourless and transparent. The ground colour of the coated object is maintained. The external appearance of the coating material is good.

----- KWIC -----

Patent Family Serial Number - PFPN (1):

11302119